

MATERIAL PROPERTY DATA SHEET




EroNet™ S75®

Short Term • Single Net • Straw Matrix • Erosion Control Blanket

DESCRIPTION

S75 temporary Erosion Control Blanket is composed of a 100% weed free agricultural straw matrix mechanically (stitch) bonded on two-inch centers to a single synthetic, photodegradable net. The net is secured to the top of the RECP to restrain the straw matrix once installed. S75 blanket is intended for use in applications requiring erosion protection for a period up to twelve months. The material is fully degradable. The net and thread are photodegradable and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



Each roll of S75 is made in the USA and manufactured under Western Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

Material Content

Matrix	Straw		
Netting	Lightweight, Synthetic Regular Degradable	Single Net (Green)	
Thread	Synthetic, Regular Degradable		

Standard Roll Sizes

Width	8 ft (2.4 m)	16 ft (4.9 m)
Length	112 ft (34.1 m)	563 ft (171.0 m)
Weight ± 10%	50 lb (22.7 kg)	500 lb (227.0 kg)
Area	100 sy (83.6 m ²)	1000 SY (836.0 m ²)

Material available in custom roll sizes

Approvals & Classification

Classification	FHWA: Type 2.C / ECTC: Type 2.C
TTI Approvals	Class 1 Type A, B
NTPEP Number	ECP-2020-01-18

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2023, North American Green is a registered trademark from Western Green. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.



Index Property Test Method Typical

Thickness	ASTM D6525	0.28 in. (7 mm)
Mass/Unit Area	ASTM D6566	8.0 oz/sy (275 g/sm)
Tensile Strength – MD	ASTM D6818	110 lbs/ft (1.6 kN/m)
Tensile Strength – TD	ASTM D6818	60 lbs/ft (0.9 kN/m)
Elongation - MD	ASTM D6818	30%
Elongation – TD	ASTM D6818	30%
Density/Specific Gravity	D792	N/A
Light Penetration	ASTM D6567	15%
Biomass Improvement	ASTM D7322	375%
Water Absorption	ASTM D1117	400%

Design Parameters

Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.02	N/A
Slope Maximum Gradient ¹	3H:1V	N/A
Permissible Shear Stress ²	1.6 psf (75 Pa)	N/A
Permissible Velocity ²	5.0 fps (1.5 m/s)	N/A

Manning's n Roughness (HEC-15)

τ_{lower}	τ_{mid}	τ_{upper}
0.040	0.030	0.030

1 Maximum Gradient a recommendation for typical installations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

Rev. 4.2023

Scan for additional and updated product information, or [click here](#).

