

# MATERIAL PROPERTY DATA SHEET




## BioNet® SC150BN™

Extended Term • Double Net • Coconut/Straw Matrix • Biodegradable • Erosion Control Blanket

### DESCRIPTION

SC150BN Extended Term Erosion Control Blanket consists of 30% coconut fibers and 70% weed free agricultural straw manufactured into a continuous matrix. The coconut/straw matrix is confined by a biodegradable, jute/scrim net on top and bottom, mechanically (stitch) bound on two-inch centers with a biodegradable, cotton thread. SC150BN is intended for slope and channel erosion control applications requiring up to twenty-four months of functional longevity. The material is fully degradable. The net, thread, and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



Each roll of SC150 is made in the USA and manufactured under Western Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

### Material Content

Matrix	Straw/Coconut		
Netting	Top & Bottom Net : Jute Scrim, Biodegradable, Leno Weave	Double Net	
Thread	Biodegradable Cotton or Rayon		

### Standard Roll Sizes

Width	8 ft (2.4 m)	16 ft (4.9 m)
Length	112 ft (34.1 m)	563 ft (171.0 m)
Weight ± 10%	53 lb (24.1 kg)	530 lb (241.0 kg)
Area	100 sy (83.6 m <sup>2</sup> )	1000 SY (836.0 m <sup>2</sup> )

Material available in custom roll sizes

### Approvals & Classification

Classification	FHWA: Type 3.B / ECTC: Type 3.B
TTI Approvals	N/A
NTPEP Number	ECP-2020-01-019

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2023, North American Green is a registered trademark from Western Green. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.



### Index Property Test Method Typical

Thickness	ASTM D6525	0.30 in. (8 mm)
Mass/Unit Area	ASTM D6566	8.5 oz/sy (290 g/sm)
Tensile Strength – MD	ASTM D6818	210 lbs/ft (3.1 kN/m)
Tensile Strength – TD	ASTM D6818	190 lbs/ft (2.8 kN/m)
Elongation - MD	ASTM D6818	15%
Elongation – TD	ASTM D6818	15%
Density/Specific Gravity	D792	N/A
Light Penetration	ASTM D6567	12%
Biomass Improvement	ASTM D7322	500%
Water Absorption	ASTM D1117	350%

### Design Parameters

Property	Unvegetated	Vegetated <sup>3</sup>
RUSLE C Factor <sup>2</sup>	0.03	N/A
Slope Maximum Gradient <sup>1</sup>	2H:1V	N/A
Permissible Shear Stress <sup>2</sup>	2.1 psf (100 Pa)	N/A
Permissible Velocity <sup>2</sup>	8.0 fps (2.4 m/s)	N/A

### Manning's n Roughness (HEC-15)

$\tau_{lower}$	$\tau_{mid}$	$\tau_{upper}$
0.045	0.036	0.031

1 Maximum Gradient a recommendation for typical installations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

Rev. 4.2023

Scan for additional and updated product information, or [click here](#).

