

## Material and Performance Specification American-Made Coir Log 5 lb Density, Natural Net

Description
The coir log shall be a machine-produced log of 100% coir fiber. The interior structure of the coir log shall consist of uniformly machine compressed non-woven coir fiber encased by a tubular woven and knotted natural net with net aperture of 1.5 in x 1.5 in (3.8 x 3.8 cm).

Material Content		
Matrix	100% compressed coconut coir fiber	5 lbs/ft <sup>3</sup> (80 kg/m <sup>3</sup> )
Netting	Tubular, woven coir net	

Index Property	Test Method	Typical
Density		5 lbs/ft <sup>3</sup> (80 kg/m <sup>3</sup> )
Net Thickness	ASTM D6520	>0.25 in (0.64 cm)
Net Grab Tensile	ASTM D4632	100 lbs minimum
Coir Fiber Moisture		15% maximum
Allowable Foreign Material		3% maximum
Permeability	ASTM D2434	> 16.3 cm-sec

Standard Log Specifications				
Designation	08CN5	12CN5	16CN5	20CN5
Diameter	8.0 in (20.3 cm)	12.0 in (30.5 cm)	16.0 in (40.6 cm)	20.0 in (50.8 cm)
Length*	10.0 ft (3.05 m)	10.0 ft (3.05 m)	10.0 ft (3.05 m)	10.0 ft (3.05 m)
Weight ± 10%	18 lbs (8.2 kg)	39 lbs (17.7 kg)	70 lbs (31.8 kg)	109 lbs (49.4 kg)
* Special order size is available in 20 ft. lengths				

**Proud Participant of:**

